



## Technical Data Sheet, AMPS-650L

<b>Parameter</b>	<b>Value</b>
Hc (VSM), Oe	660 ± 25
Sigma-r, emu/g	34 ± 1.1
Sigma-m, emu/g	80 ± 2
Loss on drying, %	< 0.8
FeO, %	< 22
BET, m <sup>2</sup> /g	27 ± 2
TD, g/cc	< 0.82

Particle Shape – Acicular.