



High Quality Recordable Barium Hexaferrite


Product Range

Our range of High Quality Recordable Barium Ferrite's offer a range of advantages to you the customer. These include:

- Excellent dispersion properties
- Stable coercivity during the milling process
- High quality recordable properties
- Competitively priced

Available the following coercivities:

- 1750 Oe
- 2750 Oe
- 3700 Oe
- 4000 Oe



Product Code	MBFC - 175	MBFC - 275	MBFC - 360	MBFC - 400
Coercivity	1750	2750	3698	4000
Magnetic Saturation (emu/g)	54	54	53.34	54
Average Particle Size (um)	0.7	0.7	0.7	0.95
Specific Surface Areas (m2/g)	6.5	6.5	6.5	6.5